



Glass as Packaging Material

6.1 Introduction

Glass is defined as ‘an inorganic product of fusion which has cooled to a rigid state without crystallizing’. Glass is made by cooling a heated, fused mixture of silicates, lime and soda to the point of fusion. After cooling, it attains a condition which is continuous with, and similar to, the liquid state of that substance, but which, as a result of a reversible change in viscosity, has attained so high a degree of viscosity as to be for all practical purposes solid.

6.1.1 Glass packaging

The two main types of glass container used in food packaging are

1. Bottles, which have narrow necks,
2. Jars and pots, which have wide openings.

6.1.2 Glass containers market sectors for foods and drinks

A wide range of foods is packed in glass containers. Examples are as follows: instant coffee, dry mixes, spices, processed baby foods, dairy products, sugar preserves (jams and marmalades), spreads, syrups, processed fruit, vegetables, fish and meat products, mustards and condiments etc. Glass bottles are widely used for beers, wines, spirits, liqueurs, soft drinks and mineral waters. Within these categories of food and drinks, the products range from dry powders and granules to liquids, some of which are carbonated and packed under pressure, and products which are heat sterilized.

6.2 Glass composition

6.2.1 White flint (clear glass)

Colourless glass, known as white flint, is derived from soda, lime and silica. This composition also forms the basis for all other glass colours. A typical composition would be: silica (SiO_2) 72%, from high purity sand; lime (CaO) 12%, from limestone (calcium carbonate); soda (Na_2O) 12%, from soda ash; alumina (Al_2O_3), present in some of the other raw materials or in feldspar type aluminous material; magnesia (MgO) and potash (K_2O), ingredients not normally added but present in the other materials.

6.2.2 Pale green (half white)

Where slightly less pure materials are used, the iron content (Fe_2O_3) rises and a pale green glass is produced. Chromium oxide (Cr_2O_3) can be added to produce a slightly denser blue green colour.

6.2.3 Dark green



This colour is also obtained by the addition of chromium oxide and iron oxide. **6.2.4 Amber (brown in various colour densities)**

Amber is usually obtained by melting a composition containing iron oxide under strongly reduced conditions. Carbon is also added. Amber glass has UV protection properties and could well be suited for use with light-sensitive products.

6.2.5 Blue

Blue glass is usually obtained by the addition of cobalt to a low-iron glass. Almost any coloured glass can be produced either by furnace operation or by glass colouring in the conditioning forehearth. The latter operation is an expensive way of producing glass and commands a premium product price. Forehearth colours would generally be outside the target price of most carbonated soft drinks.

6.3 Attributes of food packaged in glass containers

The glass package has a modern profile with distinct advantages, including:

6.3.1 Quality image

Consumer research by brand owners has consistently indicated that consumers attach a high quality perception to glass packaged products and they are prepared to pay a premium for them, for specific products such as spirits and liqueurs.

6.3.2 Transparency

It is a distinct advantage for the purchaser to be able to see the product in many cases, e.g. processed fruit and vegetables.

6.3.3 Surface texture

Whilst most glass is produced with a smooth surface, other possibilities also exist, for example, for an overall roughened ice-like effect or specific surface designs on the surface, such as text or coats of arms. These effects emanate from the moulding but subsequent acid etch treatment is another option.

6.3.4 Colour

A range of colours are possible based on choice of raw materials. Facilities exist for producing smaller quantities of nonmainstream colours, e.g. Stolze's feeder colour system.

6.3.5 Decorative possibilities

Including ceramic printing, powder coating, coloured and plain printed plastic sleeving and a range of labelling options.



6.3.6 Impermeability

For all practical purposes in connection with the packaging of food, glass is impermeable.

6.3.7 Chemical integrity

Glass is chemically resistant to all food products, both liquid and solid. It is odourless.

6.3.8 Design potential

Distinctive shapes are often used to enhance product and brand recognition.

6.3.9 Heat processable

Glass is thermally stable, which makes it suitable for the hot-filling and the in-container heat sterilization and pasteurization of food products.

6.3.10 Microwaveable

Glass is open to microwave penetration and food can be reheated in the container. Removal of the closures is recommended, as a safety measure, before heating commences, although the closure can be left loosely applied to prevent splashing in the microwave oven. Developments are in hand to ensure that the closure releases even when not initially slackened.

6.3.11 Tamper evident

Glass is resistant to penetration by syringes. Container closures can be readily tamper-evidenced by the application of shrinkable plastic sleeves or in-built tamper evident bands. Glass can quite readily accept preformed metal and roll-on metal closures, which also provide enhanced tamper evidence.

6.3.12 Ease of opening

The rigidity of the container offers improved ease of opening and reduces the risk of closure misalignment compared with plastic containers, although it is recognized that vacuum packed food products can be difficult to open. Technology in the development of lubricants in closure seals, improved application of glass surface treatments together with improved control of filling and retorting all combine to reduce the difficulty of closure removal. However, it is essential in order to maintain shelf life that sufficient closure torque is retained, to ensure vacuum retention with no closure back-off during processing and distribution.

6.3.13 UV protection

Amber glass offers UV protection to the product and, in some cases, green glass can offer partial UV protection.



6.3.14 Strength

Although glass is a brittle material glass containers have high top load strength making them easy to handle during filling and distribution. Whilst the weight factor of glass is unfavourable compared with plastics, considerable savings are to be made in warehousing and distribution costs. Glass containers can withstand high top loading with minimal secondary packaging. Glass is an elastic material and will absorb energy, up to a point, on impact. Impact resistance is improved by an even distribution of glass during container manufacture and subsequent treatment.

6.3.15 Hygiene

Glass surfaces are easily wetted and dried during washing and cleaning prior to filling.

6.3.16 Environmental benefits

Glass containers are returnable, reusable and recyclable. Significant savings in container weight have been achieved by technical advances in design, manufacture and handling.

6.4 Glass and glass container manufacture

6.4.1 Melting

Glass is melted in a furnace at temperatures of around 1350°C and is homogenized in the melting process, producing a bubble-free liquid. The molten glass is then allowed to flow through a temperature controlled channel (forehearth) to the forming machine, where it arrives via the feeder at the correct temperature to suit the container to be produced. For general containers, suitable for foods and carbonated beverages, this would be in the region of 1100°C.

6.4.2 Container forming

In the feeder, the molten glass is extruded through an orifice of known diameter at a predetermined rate and is cropped into a solid cylindrical shape. The cylinder of glass is known in the trade as a *gob* and is equivalent in weight to the container to be produced. The gob is allowed to free-fall through a series of deflectors into the forming machine, also known as the IS or individual section machine, where it enters the parison. The parison comprises a neck finish mould and a parison mould, mounted in an inverted position. The parison is formed by either pressing or blowing the gob to the shape of the parison mould. The parison is then reinverted, placed into the final mould and blown out to the shape of the final mould, from where it emerges at a temperature of approximately 650°C. A container is said to have been produced by either the *press and blow* or *blow and blow* process.

In general terms, the press and blow process is used for jars and the blow and blow process for bottles. An alternative, for lightweight bottles, is the *narrow neck press*



and blow process. The press and blow process is generally best suited to produce jars with a neck finish size of $\geq 35\text{mm}$ ($\geq 1.25''$); the other two processes are more suited to produce bottles with a neck finish size of $\leq 35\text{mm}$ ($\leq 1.25''$)

The narrow neck press and blow process offers better control of the glass distribution than the blow and blow process, allowing weight savings in the region of 30% to be made.

6.4.3 Design parameters

One of the design parameters to be borne in mind when looking at the functionality of a glass container is that the tilt angle for a wide-mouthed jar should be $\geq 22^\circ$ and that for a bottle $\geq 16^\circ$. These parameters are indicative of the least degree of stability that the container can withstand.

6.4.4 Surface treatments

Once formed, surface treatment is applied to the container in two stages: hot end and cold end treatment, respectively.

6.4.5 Hot end treatment

The purpose of hot end surface treatment is to prevent surface damage whilst the bottle is still hot and to help maintain the strength of the container. The most common coating material deposited is tin oxide, although derivatives of titanium are also used. This treatment tends to generate high friction surfaces; to overcome this problem, a lubricant is added.

6.4.6 Cold end treatment

The second surface treatment is applied once the container has been annealed. Annealing is a process which reduces the residual strain in the container that has been introduced in the forming process. The purpose of the cold end treatment is to create a lubricated surface that does not break down under the influence of pressure or water, and aids the flow of containers through a high speed filling line. Application is by aqueous spray or vapour, care being taken to prevent entry of the spray into the container, the most commonly used lubricants being derivatives of polyester waxes or polyethylene. The surface tension resulting from this treatment can be measured by using Dynes indicating pens. Labelling compatibility should be discussed with either the adhesive supplier or the adhesive label supplier depending on the type of label to be used.

6.5 Thermal processing of glass packaged foods

Glass containers lend themselves to in-bottle sterilization and pasteurization for both hot and cold filled products. Subject to the headspace volume conditions being maintained and thermal shock ground rules being observed, no problems will be



experienced.

In general terms, hot-fill products filled at 85°C and then cooled will require a minimum headspace of 5%, whilst a cold filled product requiring sterilization at 121°C will require a 6% minimum head space. In all cases the recommendations of the closure supplier should be obtained before preparing the design brief. It should be noted that the thermal shock of glass containers is twice as high when cooling down as when warming up. To avoid thermal shock, cool down differentials should not exceed 40°C and warm up differentials should not exceed 65°C.

Internal pressure resistance. A well-designed glass container can withstand an internal pressure of up to 10 bar (150 pounds per square inch), although the norm required rarely exceeds 5 bar. It is also capable of withstanding internal vacuum conditions and filling of thick concentrates, with steam-flushing of the headspace to produce the initial vacuum requirements for the closure seal.

6.6 Packing – due diligence in the use of glass containers

6.6.1 Receipt of deliveries

Glass containers are usually delivered on bulk palletized shrink-wrapped pallets. A check should be made for holes in the pallet shroud and broken glass on the pallet, and any damaged pallets rejected.

6.6.2 Storage/on-site warehousing

Pallets of glass must not be stored more than six high, they must be handled with care and not shunted. Fork-lift trucks should be guarded to prevent the lift masts contacting the glass. Where air rinser cleaning is used on the filling line, the empty glass containers should not be stored outside. Pallets damaged in on-site warehousing must not be forwarded to the filling area until they have been cleared of broken glass.

6.6.3 Depalletization

Plastic shrouds must be removed with care to prevent damage to the glass; if knives are used, the blade should be shrouded at all times, so as not to damage the glass. It is necessary to ensure that the layer pads between the glass containers are removed in such a way as to prevent any debris present from dropping onto the next layer of glass.

6.6.4 Cleaning operation

- *Air rinse.* The glass must be temperature-conditioned to prevent condensate forming on the inside, which would inhibit the removal of cardboard debris. The air pressure should be monitored to ensure that debris is not suspended



and allowed to settle back into the container.

- *On-line water rinse.* Where hot-filling of the product takes place, it is essential to ensure that the temperature of the water is adequate to prevent thermal shock at the filler, i.e. not more than 60°C differential.
- *Returnable wash systems.* The washer feed area must be checked to ensure that the bottles enter the washer cups cleanly. A washer-full of bottles must not be left soaking overnight. In the longer term this would considerably weaken the container and could well create a reaction on the bottle surface between the hot end coating and the caustic in the washer. Where hot-filling is taking place, it is necessary to ensure that the correct temperature is reached to prevent thermal shock at the filler.

6.6.5 Filling operation

Clean-up instructions should be issued and displayed. It is essential to ensure that flood rinsing of the filler head in question is adequate to prevent contamination of further bottles. It is necessary to ensure that filling levels in the container comply with trading standards' requirements for measuring containers.

6.6.6 Capping

Clean-up instructions on the procedure to follow should breakage occur in the capper should be issued and displayed, and all breakages recorded. The application torque of the caps and vacuum levels must be checked at prescribed intervals, as must the cap security of carbonated products.

6.6.7 Pasteurization/sterilization

It is necessary to ensure that cooling water in the pasteurizer or sterilization retort does not exceed a differential of more than 40°C (104°F), to prevent thermal shock situations. The ideal temperature of the container after cooling is 40°C, which allows further drying of the closure and helps prevent rusting of metal closures. Air knives should be used to remove water from closures to further minimize the risk of rusting.

6.6.8 Labelling

Where self-adhesive labels are to be used, all traces of condensate must be eliminated to obtain the optimum conditions for label application. Adhesives must not be changed without informing the glass supplier, since this could affect the specification of adhesives/surface treatments.

6.6.9 Distribution

It is essential to ensure that the arrangement of the glass containers in the tray, usually plastic or corrugated fibreboard, is adequate to prevent undue movement during distribution, that the shrink-wrap is tight and that the batch coding is correct and



visible.

6.6.10 Warehousing

The pallets of filled product must be carefully stacked to prevent isolated pockets of high loading that might create cut through in the lining compound of the container closures, as this would result in pack failures.

6.6.11 Quality management

The procedures of good management practice in the development, manufacture, filling, closing, processing (where appropriate), storage and distribution of food products in glass containers discussed in this chapter have been developed to ensure that product quality and hygiene standards are achieved along with consumer and product safety needs. Their application indicates *due diligence* in meeting these needs. It is essential that all procedures are clearly laid down, training is provided in their use and that regular checks are made on their implementation.

6.7 Environmental profile

6.7.1 Reuse

Glass containers can be reused for food use. The daily doorstep delivery of fresh milk in bottles and the collection of the empty bottles in the UK and collection of empty bottles of carbonated beverage are well established examples. There are wide disparities in the number of trips that can be expected depending on the location, with around 12 trips per bottle being the national average.

6.7.2 Recycling

Glass is one of the easiest materials to be recycled because it can be crushed, melted and reformed an infinite number of times with no deterioration of structure. It is the only packaging material that retains all its quality characteristics when it is recycled.

6.7.3 Reduction – lightweighting

In the period 1992–2002, it is claimed that the average weight of glass containers has been reduced by 40–50%.

6.8 Glass as a marketing tool

Glass packaging supports brand differentiation and product identification

- by the use of: · Creative and unique shapes and surface textures
- Ceramic printing, acid etching and coating
- Labelling, both conventionally and by plastic shrink sleeving

Current developments include the use of metallic, thermochromic, photochromic finishes, UV activated fluorescent and translucent inks and the ability to incorporate



UNIT 2 RIGID PACKAGING MATERIALS



embossed, foiled, velvet textured and holographic materials. These finishes are compatible with laser etching and offer the possibility of permanent traceability coding.